

<i>Document Type</i>	<i>Code</i>	<i>Date</i>	<i>Version</i>
Technical Data Sheet	Z-200/012.01	01.09.2022	01

<i>Material Category</i>	<i>Material / Product Specification</i>
Woven Fabrics	Woven Agrotextile

	Weight	Strength		Elasticity		CBR Test	Water Permeability	Hole Size $O_{90}$
<i>Method</i>	ČSN EN 965	ČSN EN ISO 10319		ČSN EN ISO 10319		ČSN EN ISO 12236	ČSN EN ISO 11058	ČSN EN ISO 12956
<i>Unit</i>	$g/m^2$	$kN/m$	$kN/m$	%	%	N	$l/s.m^2$	$\mu m$
<i>Direction</i>		MD	CD	MD	CD			
	$90 \pm 5\%$	20 -2	11 -1,1	13 $\pm 3$	12 $\pm 3$	2100 -210	20	20 $\pm 7$
	$100 \pm 5\%$	20 -2	14 -1,4	13 $\pm 3$	12 $\pm 3$	2350 -300	19	20 $\pm 7$
	$130 \pm 5\%$	20 -2	21 -2,1	13 $\pm 3$	12 $\pm 3$	3000 -300	20	20 $\pm 8$

*Comment*

For and on behalf of Milmar, spol. s r.o.



Milan Polouček, Managing Director

The above data are based on the knowledge available at the time of printing and may be subjected to amendments due to changes of the methods of manufacturing. The figures are reported as typical values only and should therefore not be taken as a guarantee of performance. Milmar, spol. s r.o. reserves the right to improve the product and adjust the specification without any further notice.