

| Document Type | Code | | Date | Version |
|----------------------|----------------------------------|---------|------------|---------|
| Technical Data Sheet | Z-200 | /184.01 | 01.09.2022 | 01 |
| | | | | |
| | | | | |
| Material Category | Material / Product Specification | | | |
| Plastic Netting | ST060-90 | | | |
| | | | | |
| | | | | |
| | Unit | | | |
| Mesh Structure | - | Diamond | | |
| Polymor | | DE | | |

| | UTIL | | |
|----------------------------------|-------|----------------------|--|
| Mesh Structure | - | Diamond | |
| Polymer | - | PE | |
| Colour | - | Brown | |
| UV Stability | - | No | |
| Width | mm | 40 - 50 | |
| Layflat | | | |
| Length | m | 25.0 – 25.5 | |
| Joint Thickness | | | |
| Weight | gr/lm | 58 - 60 | |
| Mesh Size – Machine Direction | mm | 35 - 37 (= 4 meshes) | |
| Mesh Size - Transverse Direction | | | |
| Tensile Strength - MD | | | |
| Tensile Strength - TD | | | |
| | | | |

Comment

For and on behalf of Milmar, spol. s r.o.

- Soft and formable at temperatures from 40 $^{\circ}$ C to + 85 $^{\circ}$ C
- Resistant to grease, oil, water, and some acids
- Reusable

Milan Polouček, Managing Director

The above data are based on the knowledge available at the time of printing and may be subjected to amendments due to changes of the methods of manufacturing. The figures are reported as typical values only and should therefore not be taken as a guarantee of performance. Milmar, spol. s r.o. reserves the right to improve the product and adjust the specification without any further notice.

